

PanFlor®

Technical Data Sheet
July 2020

Physical Properties	Test Method	Results
Weight	ASTM D792	76 oz/yd ² +/- 8 oz (2575 g/m ² +/- 260 g)
Flammability	14 CFR 25.853 (a) (12 Second Vertical Burn)	PASS
Gauge	Measured Prior To Texturing	0.079 inch +/- 0.005 (2.0 mm +/- 0.1)
Abrasion Resistance	ASTM D4060 (H-18, 1000g, 1000 cycles)	< 240 mg
<i>Slip Resistant Properties: PanFlor with or without Grit (dependent on texture)</i>		
Coefficient of Friction – Sliding Friction		
FAA	14 CFR 25.793 Amdt. 25–51	PASS
BOEING	BMS 8-286E Para. 8.9	PASS
AIRBUS	ISO 8295:1995	PASS
Coefficient of Friction – Static Friction		
BOEING	BMS8-286E Para. 8.8	PASS
AIRBUS	ISO 8295:1995	PASS